Technical Data Sheet

ROXUL 4 SAFE 55

Board Insulation 05080* Board Insulation 07 21 13**

Metal Wall Panels 07 42 13**

ROXUL SAFE® 55

Metal Building Insulation

Product Description & Application

ROXUL SAFE® 55 is a mineral wool insulation board approved for use in metal building assemblies where a two hour fire resistance rating is required from one side or both sides of the wall.

	Performance	Test Standard
Compliance	Mineral Fiber Block and Board Thermal Insulation - Type IVB Compliant	ASTM C612
Reaction to Fire	Flame spread index = 0; Smoke developed index = 0 Flame spread index = 0; Smoke developed index = 0 Determination of Non Combustibility of Building Materials - Non Combustible Test for Non-Combustibility - Non Combustible ULC 2 hr rated from interior side - W606 ULC 2 hr rated from both sides - W611 UL 2 hr rated from interior side - U655 UL 2 hr rated from both sides - U659 Consult UL and ULC Directories for fire rated designs	ASTM E84 (UL 723) CAN/ULC S102 CAN/ULC S114 ASTM E136
Density	Nominal Density, Minimum - 4.5 lbs/ft³ (72 kgs/m³)	ASTM C303
Thermal Resistance	R-Value / inch @ 75°F	ASTM C518 (C177)
Dimensional Stability	Linear Shrinkage - <1% @ 1200°F	ASTM C356
Corrosion Resistance	Stress Corrosion Cracking Tendency of Austenitic Stainless Steel - Passed Corrosion of Steel - Passed	ASTM C795 ASTM C665
Reaction to Moisture	Moisture Sorption - 0.04% Determination of Fungi Resistance - Passed	ASTM C1104 ASTM C1338
Thickness Dimensions	Product is available in 4" thickness (101.6mm) 24"x48" (610mm x 1219mm), 31.5"x48" (800mm x 1219mm), 32"x48" (813mm x 1219mm)	





Issued 04-01-16 Supersedes 07-05-13 NOTE: *Mast Format 1995 Edition **Master Format 2004 Edition. As ROXUL Inc has no control over installation design and workmanship, accessory materials or application conditions, ROXUL Inc. does not warranty the performance or results of any installation containing ROXUL Inc's products. ROXUL Inc's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.



ROXUL INC 8024 Esquesing Line Milton, On. L9T 6W3 tel: 800-265-6878 fax: 800-991-0110 www.roxul.com