

WMP-30

POLYPROPYLENE / SCRIM / KRAFT

Meets ASTM C1136, Type I, II, III, IV

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
White Film	Metallized Polypropylene	0.0015 inch	38.1 micron
Adhesive	Flame Resistant		
Reinforcing	Tri-directional	5 / inch (MD)	20 / 100 mm (MD)
	Fiberglass/Polyester	5 / inch (XD)	20 / 100 mm (XD)
Kraft	Natural	30 lbs / 3000 ft ²	49 g / m ²

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
Basis Weight	Scale	26 lbs / 1000 ft ²	127 g / m ²
Permeance (WVTR)	ASTM E96 Procedure A	0.02 perm (grains/hrft ² in Hg)	1.15 ng / N's
Bursting Strength	ASTM D774	70 psi	4.9 kg / cm ²
Puncture Resistance	ASTM C1136	105 beach units	3.1 Joules
Tensile Strength	ASTM C1136	55 lbs/inch width (MD)	9.6 kN / m (MD)
		40 lbs/inch width (XD)	7.0 kN / m (XD)
Caliper / Thickness	Micrometer	0.010 inch	254 micron
Accelerated Aging	30 Days @ 95% RH, 120°F (49°C)	No Corrosion	No Corrosion
		No Delamination	No Delamination
Low Temperature Resistance	ASTM D1790 -40°F (-40°C)	Remains Flexible	Remains Flexible
		No Delamination	No Delamination
High Temperature Resistance	4 hours @ 240°F (116°C)	Remains Flexible	Remains Flexible
		No Delamination	No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Mold Resistance	ASTM C665 / C1338	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.25%	0.25%
Light Reflectance	ASTM C523	85%	85%

FIRE TESTING	UL 723 / ASTM E84		CAN ULC-S102M	
	Flame Spread	Smoke Developed	Flame Spread	Smoke Developed
Film Exposed	5	5	5	5
Kraft Exposed	10	20	20	25

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

“LAMTEC” AND “WMP” ARE REGISTERED TRADEMARKS OF LAMTEC CORPORATION

Lamtec Corporation Bartley-Chester Road P.O. Box 37 Flanders, New Jersey 07836-0037 USA

Phone: (973) 584-5500
(800) 852-6832

www.lamtec.com

Fax: (973) 584-5178
(888) 852-6832