

Technical Product Information



BOARD INSULATION 07210* BOARD INSULATION 07 21 13** ACOUSTIC BOARD INSULATION 09 81 13**

General Product Information:

ROXUL® products are mineral wool fibre insulations made from basalt rock and slag. This combination results in a noncombustible product with a melting point of approximately 2150°F (1177°C), which gives it excellent fire resistance properties. ROXUL mineral wool is a water repellent yet vapour permeable material.

Description & Common Applications:

The FabRock LT™ product is a semi-rigid mineral wool insulation board that is non-combustible, lightweight, water repellent, fire resistant and sound absorbent. This product is a general all purpose board with low thermal conductivity. This board can also be fabricated to different dimensions while still retaining fire, water and thermal properties.

Compliance and Performance:

ASTM C 612 Mineral Fiber Block and Board Thermal Insulation Type IVA, Complies

Fire Performance:

ASTM E 136 Behaviour of Materials at 750°C (1382°F)

Non-Combustible CAN4 S114 Test for Non-Combustibility Non-Combustible ASTM E 84(UL 723) Surface Burning Characteristics Flame Spread = 5 Smoke Developed = 5

CAN/ULC S102 Surface Burning Characteristics Flame Spread = 5 Smoke Developed = 10

Maximum Service Temperature:

ASTM C 411 Hot Surface Performance In Compliance with

ASTM C612 @ 1200°F(650°C)

Dimensional Stability:

ASTM C 356 Linear Shrinkage 0.35% @ 1200°F (650°C)

Moisture Resistance:

ASTM C 1104 Moisture Sorption 0.03%

Fungi Resistance

ASTM C1338 Determination of Fungi Resistance Passed

Thermal Resistance:

ASTM C 518 (C 177) R-value/inch @ 75°F 4.1 hr.ft2.F/Btu

RSI value/25.4 mm @ 24°C 0.72 m²K/W

Corrosive Resistance:

ASTM C 665 Corrosiveness to Steel **Pass** ASTM C 795 **** Stainless Steel Stress Corrosion Specification as per Test Conforms


Methods C871 and C692: U.S. Nuclear Regulatory Commission,


Reg. Guide #1.36: U.S. Military Specifications MIL-I-24244 (all

versions including B and C)



Thermal Conductivity (k):





Acoustical Performance

ASTM C423 CO-EFFICIENTS AT FREQUENCIES							
Thickness	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	NRC
1.0"	0.08	0.23	0.66	0.93	1.02	1.02	0.70
1.5"	0.15	0.47	0.98	1.06	1.02	1.02	0.90
2.0"	0.26	0.68	1.14	1.13	1.06	1.07	1.00
3.0"	0.62	1.03	1.20	1.10	1.08	1.10	1.10
4.0"	1.07	1.01	1.07	1.06	1.07	1.06	1.05

Air Erosion:

UL 181 Maximum Air Velocity 1000 fpm (5.08 m/s)

Compressive Strength:

ASTM C 165 at 10% 71 psf (3.4 kPa) at 25% 209 psf (10 kPa)

Density:

ASTM C 612-00 – Actual 3.5 lb/ft³ 56kg/m³

Dimensions:

24" (width) x 48" (length) 610 mm (width) x 1219 mm (length)

36" (width) x 48" (length) 914 mm (width) x 1219 mm (length)

Thickness:

Product thickness is available in 1" to 4" in ½" increments.

*** "Provisions for lot testing may be required, consult manufacturer."

Note:

As ROXUL Inc. has no control over installation design and workmanship, accessory materials or application conditions, ROXUL Inc. does not warranty the performance or results of any installation containing ROXUL Inc's. products. ROXUL Inc's. overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.

Other ROXUL Products:

Please consult ROXUL for all your insulation needs. We have an extensive range of products for all applications from pipe insulation to commercial products to residential batts. ROXUL invites all inquiries and will act promptly to service all of your requirements.

Key Application Qualifiers:

- Easily cut
- Non-combustible
- · Excellent sound absorbency
- · Chemically inert
- · Does not rot or sustain vermin
- Does not promote growth of fungi or mildew
- · Low moisture sorption
- Water resistant
- CFC and HCFC free product and process
- · Made from natural & recycled materials

ROXUL INC. www.roxul.com Milton, Ontario Tel: 905-878-8474 Tel: 1-800-265-6878

Fax: 1-800-991-0110 Revised: October 20, 2014 Supersedes: March 31, 2010

Fax: 905-878-8077