

RADIANT ICE

Tentative Specification

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
Foil	Aluminum	0.0003 inch	7.6 micron
Film	Polyester	0.0005 inch	12.7 micron
Adhesive	Flame Resistant		
Reinforcing	Bi-directional Fiberglass	4 / inch (MD) 4 / inch (XD)	16 / 100 mm (MD) 16 / 100 mm (XD)
Foil	Aluminum	0.0003 inch	7.6 micron

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
Basis Weight	Scale	18 lbs / 1000 ft ²	88 g / m ²
Permeance (WVTR)	ASTM E96 Procedure A	0.02 perm (grains/hr-ft ² -in Hg)	1.15 ng / N's
Bursting Strength	ASTM D774	85 psi	6.0 kg / cm ²
Tensile Strength	ASTM C1136	55 lbs/inch width (MD) 55 lbs/inch width (XD)	9.6 kN / m (MD) 9.6 kN / m (XD)
Caliper / Thickness	Micrometer	0.009 inch	229 micron
Accelerated Aging	30 Days @ 95% RH, 120°F (49°C)	No Corrosion No Delamination	No Corrosion No Delamination
Low Temperature Resistance	ASTM D1790 -40°F (-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
High Temperature Resistance	4 hours @ 240°F (116°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Mold Resistance	ASTM C665	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.5%	0.5%
Emissivity	ASTM E408	0.03	0.03

FIRE TESTING

ASTM E84

Flame Spread	15
Smoke Developed	10

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

“LAMTEC” AND “WMP” ARE REGISTERED TRADEMARKS OF LAMTEC CORPORATION

5010 River Road Mount Bethel, Pennsylvania 18343-5610 U.S.A.
Phone: (570) 897-8200 Fax: (570) 897-6081 Web: www.lamtec.com