



INNOVATIONS FOR LIVING™

FOAMULAR® C-300

Extruded Polystyrene Rigid Insulation

Insulation for Perimeter of Foundation Walls for Commercial Construction



ADVANTAGES

- Exceptional thermal resistance
- Exceptional moisture resistance
- High compressive strength helps prevent insulation from being damaged during backfill
- Can be used on interior or exterior face of concrete, mechanically fastened or fully adhered
- Meets CAN/ULC S701, (Type 4)

Physical Properties	ASTM Method	FOAMULAR® C-300
Thermal Resistance	C 518 or C 177	R-5.0, ft ² h°F/BTU (0.88 m ² °C/W)
Compressive strength, min.	D 1621	30 psi (210 kPa)
Water absorption, max. (% by volume)	D 2842	0.70
Type	CAN/ULC S701	4
Thickness		1", 1.5", 2", 2.5", 3", 3.5", 4" (25.4, 38, 51, 62.5, 75, 89, 100 mm)
Sizes		24"x96" (600 mm x 2400 mm)
Edge Treatment		Ship lap or butt edge
Max. operating temperature		74 °C (165 °F)



INNOVATIONS FOR LIVING™

OWENS CORNING CANADA LP
3450 McNicoll Avenue
Scarborough, Ontario M1V 1Z5

1-800-GET-PINK®
www.owenscorning.ca



Pub. No. 300568. Printed in Canada January 2010. GREENGUARD Indoor Air Quality Certified® is Reg. U.S. Pat & TM Office. The GREENGUARD INDOOR AIR QUALITY CERTIFIED® Mark is a registered certification mark used under license through the GREENGUARD Environmental Institute. Owens Corning PINK insulation is GREENGUARD Certified for indoor air quality, except bonded loosefill products. The colour PINK is a registered trademark of Owens Corning. © 2010 Owens Corning. All Rights Reserved. LEED is a registered trademark of U.S. Green Building Council.