

WMP-50 BLACK

BLACK COATED POLYPROPYLENE / SCRIM / CORE / METALLIZED POLYESTER

Meets ASTM C1136 Type I, II, III, IV, V, VI

FACING COMPOSITION	DESCRIPTION	VALUES (I-P)	VALUES (SI) METRIC
Black Coated Film	Metallized Polypropylene	17.6 lbs / 3000 ft ²	29 g / m ²
Adhesive	Flame Resistant		
Reinforcing	Tri-directional	MD: 5 / inch	MD: 20 / 100 mm
	Fiberglass / Polyester	XD: 5 / inch	XD: 20 / 100 mm
Core	Proprietary	30 lbs / 3000 ft ²	49 g / m ²
Adhesive	Polymeric		
Film	Metallized Polyester	0.0005 inch	12.7 micron

PHYSICAL PROPERTIES	TEST METHOD	VALUES (I-P)	VALUES (SI) METRIC
Basis Weight	Scale	33 lbs / 1000 ft ²	161 g / m ²
Permeance (WVTR)	ASTM E96 Procedure A	≤0.02 perm (grains / hr*ft ² *in Hg)	≤1.14 ng / m ² · s · Pa
Bursting Strength	ASTM D774	120 psi	8.4 kg / cm ²
Tensile Strength	ASTM D828	MD: 65 lbs / inch XD: 60 lbs / inch	MD: 11.4 kN / m XD: 10.5 kN / m
Temp. & Humidity Resistance	ASTM C1258	No Corrosion	No Corrosion
Low Temperature Resistance	ASTM C1263 4 hours at -20°F (-29°C)	No Delamination	No Delamination
High Temperature Resistance	ASTM C1263 Modified 4 hours at 240°F (116°C)	Remains Flexible	Remains Flexible
Mold Resistance	ASTM C1338	No Delamination	No Delamination
Dimensional Stability	ASTM D1204	No Growth	No Growth
		≤0.5%	≤0.5%

FIRE TESTING

ASTM E84 / UL 723

Film Side Kraft Side

Flame Spread	5	5
Smoke Developed	30	20



Physical property values are typical and not intended to serve as specifications.
Weight and thickness values +/- 10%. Information subject to change without notice.

“LAMTEC” AND “WMP” ARE REGISTERED TRADEMARKS OF LAMTEC CORPORATION

5010 River Road Mount Bethel, Pennsylvania 18343-5610 U.S.A.
Phone: (570) 897-8200 Fax: (570) 897-6081 Web: www.lamtec.com